

## OK Tigrod 4043

OK Tigrod 4043 is one of the most widely used welding alloys. The alloy is used for welding AlMgSi - types and AlSi - alloys with up to 7 % Silicon. Not recommended for anodizing. Non-Heat treatable.

<b>Classifications Wire Electrode</b>	SFA/AWS A5.10 : R4043 EN ISO 18273 : S Al 4043 (AlSi5) JIS Z 3232 : A4043
<b>Approvals</b>	CWB AWS A5.10/A5.10M:2012 (ER4043) CE EN 13479 DB 61.039.06 JIS JIS Z 3232

*Approvals are based on factory location. Please contact ESAB for more information.*

<b>Alloy Type</b>	AlSi
<b>Shielding Gas</b>	I1, I3 (EN ISO 14175)

### Typical Wire Composition %

Mn	Si	Al	Cu	Ti	Fe	Zn
0.01	5.00	Rem	0.02	0.01	0.14	0.01